

PI 1178330

REC'D 09 JUN 2004

WIPO

PCT

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office

June 07, 2004

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE.

APPLICATION NUMBER: 60/320,056

FILING DATE: March 26, 2003

RELATED PCT APPLICATION NUMBER: PCT/US04/09019

By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS



N. Woodson
N. WOODSON
Certifying Officer

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

Electronic Filing System (EFS) Data
Electronic Patent Application Submission
USPTO Use Only

EFS ID: 25222
Application ID: 60320056
Title of Invention: Tungsten-based Electrocatalyst
and Fuel Cell Containing Same
First Named Inventor: Joel Christian
Domestic/Foreign Application: Domestic Application
Filing Date: null
Effective Receipt Date: 2003-03-26
Submission Type: Provisional Application
Filing Type: new-utility
Confirmation Number: 0
Attorney Docket Number: 03-2-308
Digital Certificate Holder: cn=Robert Francis Clark, ou=Registered Attorneys, ou=Patent and
Trademark Office, ou=Department of Commerce, o=U.S.
Government, c=US
Certificate Message Digest: VsUj+YkqpaOk+QZfxeHNKQ==
Total Fees Authorized: \$160.0
Payment Category: DA - Deposit Account
Deposit Account Number: 150685
Deposit Account Name: Robert F. Clark



TRANSMITTAL FORM

Electronic Version 1.0.3

Stylesheet Version: 1.0

Submission Type: Provisional
Application

Attorney Docket
Number:

03-2-
308

Tungsten-based Electrocatalyst and Fuel Cell Containing Same

First Named Inventor: Joel B. Christian

SUBMITTED BY

Name:

Robert F. Clark

Registration Number:

33853

Electronic Signature Mark: RFClark

Date Signed: 20030326

I certify that the use of this system is for OFFICIAL correspondence between patent applicants or their representatives and the USPTO. Fraudulent or other use besides the filing of official correspondence by authorized parties is strictly prohibited, and subject to a fine and/or imprisonment under applicable law.

I, the undersigned, certify that I have viewed a display of document(s) being electronically submitted to the United States Patent and Trademark Office, using either the USPTO provided style sheet or software, and that this is the document(s) I intend for initiation or further prosecution of a patent application noted in the submission. This document(s) will become part of the official electronic record at the USPTO.

Attached Files:

specification

03-2-308provisional.xml

bibd-transmittal

03-2-308provapds.xml

fee-transmittal

03-2-308provfee.xml

Comments:

FEE TRANSMITTAL

Electronic Version 1.1.0

Stylesheet Version: 1.0

Patent fees are subject to annual revisions on or about October 1st of each year.

Large Entity

TOTAL FEES AUTHORIZED: \$ 160

The commissioner is hereby authorized to charge indicated processing and/or publication fees and credit any overpayments to:

Deposit Account Number: 15-0685



Deposit Account Name: OSRAM SYLVANIA Inc.

Charge Any Additional Fee Required Under 37 C.F.R. Sections 1.16 and 1.17.

Charge Assignment Fees Required Under 37 C.F.R. Section 1.21 (h).

SUBMITTED BY

Authorized Name: Robert F. Clark

Electronic Signature Mark: RFClark

Date Signed: 20030326

BASIC FILING FEE

Fee Description	Fee Code	Fee Paid
Provisional Filing Fee	1005	\$ 160

Subtotal For Basic Filing Fee: \$ 160

APPLICATION DATA SHEET

Electronic Version 0.0.11

Stylesheet Version: 1.0

Attorney Docket Number: 03-2-308

Publication Filing Type: new-utility

Application Type: utility

Title of Invention: Tungsten-based Electrocatalyst and Fuel Cell Containing Same

Legal Representative:

Attorney or Agent: Robert F. Clark

Registration Number: 33853

Customer Number Correspondence Address: 24252



INVENTOR(s):

Primary Citizenship: USA

Given Name: Joel

Middle Name: B.

Family Name: Christian

Residence City: Towanda

Residence State: PA

Residence Country: US

Address: 37 Third St.
Towanda PA, US

SPECIFICATION

Electronic Version 1.2.8

Stylesheet Version 1.0

Tungsten-based Electrocatalyst and Fuel Cell Containing Same

Background of Invention

[0001] Transition metal carbides have been studied as catalysts since 1959. In 1965, AEG-Telefunken discovered that tungsten carbide could potentially replace platinum as an anode catalyst for acid style fuel cells. These investigators ran a fuel cell for over 30,000 hours with an anode catalyst composed of tungsten carbide. Since that time, five tungsten compounds have been identified as potential anode and cathode catalysts for low-temperature acid fuel cells: WC, W_2C , WO_3 , Pt , Na_xWO_3 , W-POM.

Summary of Invention

[0002] The catalyst of this invention is a non-stoichiometric tungsten compound, $H_{0.53}WO_3$, which may be used as both anode and cathode electrocatalyst for acid-style low-temperature fuel cells.

[0003] The method used to make the catalyst is a novel route to hydrogen tungsten bronze which involves first creating an ammonium bronze, $(NH_4)_{0.33}WO_3$. This material is stable and is formed easily by heating AMT to 490 °C in an inert atmosphere. This method has many practical improvements in the art, including eliminating extra water and oxygen from the compound, and forming a stable intermediate for further catalyst synthesis. This intermediate can also be applied to synthesis for other tungsten-based catalyst applications, including hydrocracking and NO_x control catalysts.

Brief Description of Drawings

[0004] Fig. 1 is an x-ray diffraction pattern of the catalyst of this invention.

- [0005] Fig. 2 is a plot of the half-cell performance of the catalyst of this invention.
- [0006] Fig. 3 is graph of the voltage-power performance of a fuel cell wherein both the anode and cathode are comprised of the tungsten-based catalyst of this invention.
- [0007] Fig. 4 is a graph of the operational performance of a fuel cell at various resistive loads wherein both the anode and cathode are made with the tungsten-based catalyst of this invention.

Detailed Description

- [0008] The tungsten-based catalyst of this invention was synthesized and tested by XRD, voltammetry, and fuel cell operation. Figure 1 shows the X-ray powder diffraction pattern of the carbon-supported tungsten-based electrocatalyst used for fuel cell demonstration. The pattern fits PDF 72-1712, $H_{0.53}WO_3$. Figure 3 shows the performance of a fuel cell wherein both the anode and cathode have been fabricated with the tungsten-based catalyst of this invention.
- [0009] *EXAMPLE 1*
- [0010] Three carbon rods (Bay Carbon AGKSP 0.242x12) were soaked in a solution of ammonium metatungstate (AMT) (OSRAM SYLVANIA, catalyst grade, 1600g/l) for three days. The rods were placed in a 9" Inconel boat, along with a small amount of AMT in a graphite boat as a visual indicator. The boats were placed in a tube furnace and sealed at a pressure of 5 inches water gauge in flowing Argon.
- [0011] The furnace was heated to 200 ° C and held until the AMT powder appeared green, indicating the material had dried. The temperature was raised to 490 ° C under argon and held overnight. The samples appeared dark blue, indicating that an ammonium tungsten bronze had formed.
- [0012] The gas flow was changed to 1 lpm H₂ and 1 lpm Ar to provide a partially reducing atmosphere. The appearance of the material was monitored, and the AMT sample appearance changed color with a moving interface, changing from blue to gray. After 7.5 hours, the furnace was cooled. The furnace was purged and the samples removed for analysis. One rod was labeled "S5." Figure 2 shows the ½ cell performance characteristic for sample S5.

[0013] *EXAMPLE 2*

[0014] Four carbon rods (Bay Carbon AGKSP 0.242x12) were soaked in a solution of ammonium metatungstate (AMT) (OSRAM SYLVANIA, catalyst grade, 1600g/l) for three days. The rods were placed in a 9" Inconel boat, along with two other boats, one ceramic boat containing 20wt% AMT on a high-surface-area carbon powder, Cabot XC-72, and one ceramic boat containing a small amount of AMT as a visual indicator. The boats were placed in a tube furnace and sealed at a pressure of 5 inches water gauge in flowing Argon.

[0015] The furnace was heated to 120 ° C and held until the AMT powder appeared green, indicating the material had dried. The temperature was raised to 490 ° C under argon and held overnight. The samples appeared dark blue, indicating that an ammonium tungsten bronze had formed.

[0016] The gas flow was changed to 1 lpm H₂ and 3.5 SCFH Ar to provide a partially reducing atmosphere. The appearance of the material was monitored, and the AMT sample appearance changed color with a moving interface, changing from blue to gray. After 1.75 hours, the furnace was cooled. The furnace was purged and the samples removed for analysis. One rod was labeled "S6." X-ray diffraction of the center boat containing 20%W on XC-72 to start showed the material to be H_{0.53}WO₃, matching PDF 72-1712, file L242823.MDI.

[0017] *EXAMPLE 3*

[0018] The tungsten bronze supported on XC-72 from example 2 was fabricated into a 5cm² membrane-electrode-assembly (MEA). They were teflon-bonded into both catalyst layers of a 5-layer MEA with carbon paper and NafionTM 117 membrane, then assembled into a 5cm² fuel cell and operated with hydrogen and air at room temperature with a various fixed resistive loads to obtain the operation curves in Figure 4.

Claims

- [c1] An electrode for a fuel cell comprising $H_{0.53}WO_3$.
- [c2] A fuel cell comprising an anode and cathode having a catalyst wherein the catalyst consists of a tungsten-based compound.

Tungsten-based Electrocatalyst and Fuel Cell Containing Same

Abstract of Disclosure

The catalyst of this invention is a non-stoichiometric tungsten compound, $H_{0.53}WO_3$, which may be used as both anode and cathode electrocatalyst for acid-style low-temperature fuel cells.

Figures




FIG. 1




FIG. 2




FIG. 3




FIG. 4

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☒ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.